



TECHNICAL DATA SHEET

KEIM STANDARDPUTZ

1. PRODUCT DESCRIPTION

KEIM Standardputz According to DIN EN 998-1, this is a normal plastering mortar based on lime-cement with small organic additives. KEIM Standardputz corresponds to mortar category CS II, P II according to DIN V 18 550. In combination with the KEIM finishing plasters and/or KEIM silicate paints, this results in a coordinated plaster/coating system.

2. FIELD OF APPLICATION

KEIM Standardputz can be used as a base and finishing plaster for exterior, interior and damp areas. It is suitable for plastering all types of masonry with the exception of porous or highly heat-insulating lightweight building materials. Use special plaster for base are. KEIM Standardputz has outstanding machineability with excellent stability. When used as a finishing plaster, it can be textured in a KEIM Standardputz variety of ways, washed out and also felted well.

3. PRODUCT PROPERTIES

- excellent application properties
- mineral
- very robust surface
- permeable
- water-repellent
- fire behaviour: non-flammable (A1)

MATERIAL CHARACTERISTICS:

- Bulk density: approx. 1,45 g/cm³
- Maximum grain size: 1.3 mm

CLASSIFICATION:

- Plaster type: GP
- Compressive strength category: CS II 1,5 -5,0 N/mm²
- Standard compressive strength DIN EN 1015-11: DIN EN 1015-11
- Adhesive tensile strength: $\geq 0,08$ N/mm²
- Fracture pattern Adhesive tensile strength: A,B,C
- Standard Adhesive tensile strength DIN EN 1015-12: DIN EN 1015-12
- Water absorption class: W2
- Standard Water absorption DIN EN 1015-18: DIN EN 1015-18

COLOUR SHADES:

grey

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be strong, dry, clean, sound and free from adhesion-reducing residues and must not be too absorbent. In the case of highly absorbent substrates or very warm ambient conditions, prewetting must be carried out. Separating substances, e.g. shuttering oil residues on concrete surfaces, must be removed by suitable means. Equalise strong unevenness with suitable material of the same type.

APPLICATION CONDITIONS:

Ambient and substrate temperature ≥ 5 °C during application and drying. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

PREPARATION OF MATERIAL / MIXING & CONVEYING:

Mix KEIM Standardputz with approx. 6.6 - 7.0 L (specification per bag) of clean water with a power stirrer to a stiff-plastic consistency without lumps and allow to mature briefly. Do not remix already stiffened material with water. Application can be performed by hand, via continuous mixer or rendering machine. Do not overmix the material, otherwise there is a risk of a severe loss of strength. Do not remix material that has already set.

CONSUMPTION:

approx. 1,4 kg/m² per mm

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

APPLICATION:

Apply mixed KEIM Standardputz quickly with suitable tools in uniform layer thickness.

LAYERING SYSTEM:

When used as a base coat, the minimum plaster thickness is 15 mm. For plaster thicknesses greater than 20 mm per layer and other unfavourable conditions, multi-layer application is recommended, whereby the previous layer must be roughened in each case. When working with several layers, observe the intermediate standing times and do not exceed the total thickness of 30 mm for all layers.

TOP RENDER:

When used as finishing plaster, a minimum thickness of 5 mm should be observed.

When using KEIM Standardputz as finishing plaster, the surface can be felted with a sponge board after sufficient consolidation. Free texturing or washing is also possible.

If possible, treat the surface without adding water. Avoid binder accumulation on the surface.

AFTERTREATMENT:

KEIM Standardputz must be protected from drying out too quickly due to sun or wind, or kept moist if necessary.

FINISHING:

KEIM Standardputz as base plaster:

KEIM Deckputz-historisch is ideally suited as a finishing plaster.

KEIM Universalputz, KEIM Universalputz-Fein, KEIM Turado, KEIM Brillantputz and KEIM Stucasol can be used as finishing plasters.

(please observe the respective Technical Data Sheets and the standing time)

KEIM Standardputz as finishing plaster:

All KEIM coating systems for exterior and interior use are suitable.

Observe the standing time before painting. Required preparatory work on exterior surfaces: Etching with KEIM Etching Liquid, diluted 1:3 with water, then rinse with clean water.

CLEANING OF TOOLS:

Clean tools, machines and mixers immediately after use with water. In hardened state only a mechanical removal is possible.

TECHNICAL DATA SHEET – KEIM STANDARDPUTZ

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
25	kg	42	bag

6. STORAGE

max. storage time	Storage conditions
12 months	dry cool frost-free

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

Waste code: 17 01 01

8. SAFETY INSTRUCTIONS


Please, refer to the Material Safety Data Sheet.

9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

10. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.



KEIMFARBEN GMBH

Keimstraße 16 / 86420 Diedorf / Tel. +49 821 4802-0 / Fax +49 821 4802-210
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 35456 676-0 / Fax +49 35456 676-38
www.keim.com / info@keimfarben.de